

with hand and head



aPraktika

Protosil Kft

2071 Páty, Várady József u. 2.

HUNGARY



info@apraktika.hu



<https://www.apraktika.hu/en/ur5895-polyurethane-resin-ductile-small-pack>

UR 58630/5803 Polyurethane Rubber: Technical Data Sheet

The UR 5895/5805 polyurethane resin system consists of a polyol and isocyanate components that cure at room temperature and are suitable for manual processing.

The cured UR 5805/5895 polyurethane elastomer can be used to make slightly flexible finished products as well as moulds.

Main properties of the hardened product:

- Easy to process
- Has significant tear resistance
- High impact value
- Fast curing,
- Short pot life



1. Instructions for use

1. Prepare the two components (resin / base and catalyst) and mix them separately. Weigh out the amounts of polyol and isocyanate components given in the table below.
2. Keep the mixing ratio exactly. The technical properties listed below are guaranteed only this case.
3. Do not leave unmixed components on the wall of the mixing bowl.
4. Stir until the color is homogeneous. The polyurethane resin can then be cast.

Crystallization can occur with both the isocyanate and the polyol component.

In this case, i.e. if the polyol component becomes inhomogeneous and the isocyanate becomes opaque, place in a heat treatment chamber and homogenize at 60 ° C.

The system is then reusable.

Ensure the components are mixed at least 18 ° C.

2. Important Recommendations

- Observe the general health and safety regulations
- Wear protective gloves
- Ensure adequate ventilation
- Wear safety goggles and suitable safe clothing
- Surfaces in contact with the resin must be clean, dry and free from grease.
- It is recommended to heat the components above 23 °C
- The mixing ratio must not deviate from the specified maximum by 2%
- The mixing bowl must be free of moisture
- Use separator on the model
- Maintain an ambient temperature of 23 °C during curing
- 5 days of leaving at 23 °C is required to achieve maximum technical performance



3. Chemical and Physical Properties

	UR 5803 Isocyanate	UR 58630 Polyol	Mixture
Mixing ratio (weight %)	55	100	
Mixing ratio (volume %)	54	100	
Consistency	liquid	liquid	liquid
Color	amber	blue or white	blue or white
Viscosity	450	1500	1000
Density at 25 °C g/cm ³	1,21	1,19	1,25
Working time (pot life) at 25 °C			10
Hardness Shore A			94
Tensile Strength MPa			16
Elongation at break %			400
Tear strength kN/mm			64
Abrasion BASHORE %			25
Operation temperature °C			-20 / 70
Glass transition temperature °C			< 0
Disassembly hour 23 °C / 80 °C			12 / 1
Maximum casting thickness (mm)			100

with hand and head



aPraktika

The cured finished product must not be classified as dangerous in accordance with Directive 88/379 / EEC and subsequent amendments. The hazards of the components can be seen in another document.

4. Shelf Life

The F180 polyurethane resin is guaranteed for a period of 18 months if stored correctly at a temperature of between 5°- 27°C (41° - 80°F).

The advice given verbally, in writing or through demonstrations on the use of the products are based on our knowledge.

The use and application of the product by the user lie beyond the control of the company and are therefore the user's own responsibility.