

with hand and head



aPraktika

Protosil Kft

2071 Páty, Várady József u. 2.

HUNGARY



info@apraktika.hu



<https://www.apraktika.hu/en/smooth-cast-onyx-slow>

Smooth Cast Onyx Slow Polyurethane Resin: Technical Data Sheet

This deep black, mercury-free fastcast polyurethane resin system consists of polyol and isocyanate components that cure at room temperature and are recommended for manual processing.

Due to its relative low price and black base color, it is suitable for home projects, making black figurines and plaques.

Main properties of the hardened product:

- 8-10 minutes pot time
- Deep black base color
- Easy to use, 1: 1 volume ratio
- Very low aggression against silicones
- High polishable
- Odorless
- Extremely low viscosity, bubble-free casting



1. Instructions for use

1. Prepare the two components (resin / base and catalyst) and mix them separately. Weigh out the amounts of polyol and isocyanate components given in the table below. You can use a simple syringe for volume and pocket scale for weight.
2. Keep the mixing ratio exactly. The technical properties listed below are guaranteed only this case.
3. Do not leave unmixed components on the wall of the mixing bowl.
4. Stir at least for 1 minute to achieve the best result. The polyurethane resin can then be cast.

After disassembly allow the object to rest at room temperature for 24 hours.

The casting achieves the maximum technical properties and heat resistance if it is then heat-treated at 65 ° C for 4-6 hours.

Crystallization can occur with both the isocyanate and the polyol component.

After opening the bottles possibly use up the resin. Otherwise store under vacuum or oxygen-free environment to keep the resin usability longer.

Ensure the components are mixed at least 18 °C.

2. Important Recommendations

- Observe the general health and safety regulations
- Wear protective gloves
- Ensure adequate ventilation
- Wear safety goggles and suitable safe clothing



3. Chemical and Physical Properties

	Poliol	Isocianát	Keverék
Mixing ratio by volume %	100	100	
Mixing ratio by weight %	100	120	
Consistency	liquid	liquid	
Colour	deep black	deep black	deep black
Viscosity at 25 °C (mPas)			100
Density (g / cm ³) 25 °C			1,09
Pot life at 25 °C (minutes)			5
Hardness Shore A			80
Flexural modulus of elasticity MPa			19,28
Flexural strength MPa			70,5
Tensile strength MPa			52,8
Modulus of elasticity MPa			2575
Elongation at break %			3 %
Compressive strength MPa			78,5
Compressive modulus of elasticity MPa			674
Bending temperature, °C			100
Disassembly time (minutes) after gelation 25 °C,			90 min.
Shrinkage %			1,2



The cured finished product is not classified as dangerous in accordance with Directive 88/379 / EEC and subsequent amendments. The hazards of the components can be seen in another document.

4. Shelf Life

Th Smooth Cast Onyx Slow polyurethane resin is guaranteed for a period of 6 months if stored correctly at a temperature of between 5°- 27°C (41° - 80°F).

Polyurethane resins are sensitive to the oxygen and moisture content of the air, so try for use up as soon as possible.

Isocyanate is light sensitive and should be stored in a dark, airtight or nitrogen-rich container.

Be careful not to interchange the closing caps.

The advice given verbally, in writing or through demonstrations on the use of the products are based on our knowledge.

The use and application of the product by the user lie beyond the control of the company and are therefore the user's own responsibility.